

Model #1271 - Double Hung Tilt Energy Ratings

| Glass Options | Glazing | Gas | Grille | Energy Star Zone(s) | | ER | SHGC | VT | CR | U-Value (Metric) | U-Value Imp (Imperial) | R-Value (Imperial) |
|----------------------|---------|---------|--------|---------------------|-----------|----|------|------|----|---------------------|---------------------------|-----------------------|
| | | | | Canada | US | | | | | | | |
| 366 (2) | Double | | | None | C,SC,S | 12 | 0.21 | 0.48 | 56 | 1.76 | 0.31 | 3.23 |
| 366 (2) | Double | | Y | None | C,SC,S | 11 | 0.19 | 0.43 | 56 | 1.76 | 0.31 | 3.23 |
| 366 (2) | Double | Arg/Kry | | 1 | N,NC,SC,S | 16 | 0.20 | 0.48 | 60 | 1.54 | 0.27 | 3.70 |
| 366 (2) | Double | Arg/Kry | Y | 1 | N,NC,SC,S | 16 | 0.19 | 0.43 | 60 | 1.54 | 0.27 | 3.70 |
| 366 (2) | Double | Argon | | 1 | N,NC,SC,S | 17 | 0.21 | 0.48 | 60 | 1.54 | 0.27 | 3.70 |
| 366 (2) | Double | Argon | Y | 1 | N,NC,SC,S | 16 | 0.19 | 0.43 | 60 | 1.54 | 0.27 | 3.70 |
| Bronze/LOF (3) | Double | | | None | None | 21 | 0.43 | 0.43 | 53 | 1.93 | 0.34 | 2.94 |
| Bronze/LOF (3) | Double | | Y | None | None | 19 | 0.39 | 0.38 | 53 | 1.93 | 0.34 | 2.94 |
| Bronze-LOF (3) | Double | Arg/Kry | | 1 | None | 25 | 0.43 | 0.43 | 57 | 1.76 | 0.31 | 3.23 |
| Bronze-LOF (3) | Double | Arg/Kry | Y | None | NC | 22 | 0.39 | 0.38 | 57 | 1.76 | 0.31 | 3.23 |
| Bronze-LOF (3) | Double | Argon | | 1 | None | 25 | 0.43 | 0.43 | 57 | 1.76 | 0.31 | 3.23 |
| Bronze-LOF (3) | Double | Argon | Y | None | NC | 22 | 0.39 | 0.38 | 57 | 1.76 | 0.31 | 3.23 |
| Grey-LOF (3) | Double | | | None | None | 20 | 0.41 | 0.39 | 53 | 1.93 | 0.34 | 2.94 |
| Grey-LOF (3) | Double | | Y | None | None | 18 | 0.37 | 0.34 | 53 | 1.93 | 0.34 | 2.94 |
| Grey-LOF (3) | Double | Arg/Kry | | None | None | 24 | 0.41 | 0.39 | 57 | 1.76 | 0.31 | 3.23 |
| Grey-LOF (3) | Double | Arg/Kry | Y | None | NC | 21 | 0.37 | 0.34 | 57 | 1.76 | 0.31 | 3.23 |
| Grey-LOF (3) | Double | Argon | | None | None | 24 | 0.41 | 0.39 | 57 | 1.76 | 0.31 | 3.23 |
| Grey-LOF (3) | Double | Argon | Y | None | NC | 21 | 0.37 | 0.34 | 57 | 1.76 | 0.31 | 3.23 |
| LOF (3) | Double | | | 1 2 | None | 30 | 0.58 | 0.57 | 53 | 1.93 | 0.34 | 2.94 |
| LOF (3) | Double | | Y | 1 | None | 26 | 0.51 | 0.51 | 53 | 1.93 | 0.34 | 2.94 |
| LOF (3) | Double | Arg/Kry | | 1 2 | None | 33 | 0.58 | 0.57 | 57 | 1.76 | 0.31 | 3.23 |
| LOF (3) | Double | Arg/Kry | Y | 1 2 | None | 30 | 0.52 | 0.51 | 57 | 1.76 | 0.31 | 3.23 |
| LOF (3) | Double | Argon | | 1 2 | None | 33 | 0.58 | 0.57 | 57 | 1.76 | 0.31 | 3.23 |
| LOF (3) | Double | Argon | Y | 1 2 | None | 30 | 0.52 | 0.51 | 57 | 1.76 | 0.31 | 3.23 |
| LOF-LOF (2&3) | Double | Arg/Kry | | 1 2 3 | N | 34 | 0.49 | 0.53 | 45 | 1.48 | 0.26 | 3.85 |
| LOF-LOF (2&3) | Double | Arg/Kry | Y | 1 2 | N | 31 | 0.44 | 0.47 | 45 | 1.48 | 0.26 | 3.85 |
| LOF-LOF (2&3) | Double | Argon | | 1 2 3 | N | 34 | 0.49 | 0.53 | 45 | 1.48 | 0.26 | 3.85 |
| LOF-LOF (2&3) | Double | Argon | Y | 1 2 | N | 31 | 0.44 | 0.47 | 45 | 1.48 | 0.26 | 3.85 |
| 366 (2) | Triple | Arg/Kry | | 1 | N,NC,SC,S | 16 | 0.20 | 0.44 | 63 | 1.54 | 0.27 | 3.70 |
| 366 (2) | Triple | Argon | | None | NC,SC,S | 15 | 0.20 | 0.44 | 63 | 1.59 | 0.28 | 3.57 |
| 366 (2) | Triple | Krypton | | 1 2 | N,NC,SC,S | 21 | 0.19 | 0.44 | 67 | 1.31 | 0.23 | 4.35 |
| Bronze | Triple | Arg/Kry | | None | None | 22 | 0.44 | 0.43 | 56 | 1.93 | 0.34 | 2.94 |
| Bronze | Triple | Argon | | None | None | 22 | 0.44 | 0.43 | 56 | 1.93 | 0.34 | 2.94 |
| Bronze | Triple | Krypton | | 1 | None | 25 | 0.43 | 0.43 | 59 | 1.76 | 0.31 | 3.23 |
| Bronze-LOF (5) | Triple | Arg/Kry | | 1 | N,NC | 25 | 0.40 | 0.39 | 61 | 1.65 | 0.29 | 3.45 |
| Bronze-LOF (5) | Triple | Argon | | 1 | N,NC | 25 | 0.40 | 0.39 | 60 | 1.65 | 0.29 | 3.45 |
| Bronze-LOF (5) | Triple | Krypton | | 1 2 | N,NC | 30 | 0.40 | 0.39 | 64 | 1.42 | 0.25 | 4.00 |
| Bronze-LOF-LOF (3&5) | Triple | Arg/Kry | | 1 | N,NC | 27 | 0.37 | 0.37 | 64 | 1.48 | 0.26 | 3.85 |
| Bronze-LOF-LOF (3&5) | Triple | Argon | | 1 2 | N,NC | 27 | 0.37 | 0.37 | 64 | 1.48 | 0.26 | 3.85 |
| Bronze-LOF-LOF (3&5) | Triple | Krypton | | ABC | N,NC | 32 | 0.37 | 0.37 | 68 | 1.25 | 0.22 | 4.55 |
| Grey | Triple | Arg/Kry | | None | None | 20 | 0.42 | 0.39 | 56 | 1.93 | 0.34 | 2.94 |
| Grey | Triple | Argon | | None | None | 20 | 0.42 | 0.39 | 56 | 1.93 | 0.34 | 2.94 |
| Grey | Triple | Krypton | | None | None | 24 | 0.41 | 0.39 | 59 | 1.76 | 0.31 | 3.23 |

Model #1271 - Double Hung Tilt Energy Ratings

| Glass Options | Glazing | Gas | Grille | Energy Star Zone(s) | | ER | SHGC | VT | CR | U-Value (Metric) | U-Value Imp (Imperial) | R-Value (Imperial) |
|--------------------|---------|---------|--------|---------------------|------|----|------|------|----|---------------------|---------------------------|-----------------------|
| | | | | Canada | US | | | | | | | |
| Grey-LOF (5) | Triple | Arg/Kry | | None | N,NC | 24 | 0.38 | 0.36 | 61 | 1.65 | 0.29 | 3.45 |
| Grey-LOF (5) | Triple | Argon | | None | N,NC | 24 | 0.38 | 0.36 | 60 | 1.65 | 0.29 | 3.45 |
| Grey-LOF (5) | Triple | Krypton | | 1 2 | N,NC | 29 | 0.38 | 0.36 | 64 | 1.42 | 0.25 | 4.00 |
| Grey-LOF-LOF (3&5) | Triple | Arg/Kry | | 1 | N,NC | 26 | 0.35 | 0.33 | 64 | 1.48 | 0.26 | 3.85 |
| Grey-LOF-LOF (3&5) | Triple | Argon | | 1 | N,NC | 26 | 0.35 | 0.33 | 64 | 1.48 | 0.26 | 3.85 |
| Grey-LOF-LOF (3&5) | Triple | Krypton | | 1 2 | N,NC | 31 | 0.35 | 0.33 | 68 | 1.25 | 0.22 | 4.55 |
| LOF (5) | Triple | Arg/Kry | | 1 2 | N | 33 | 0.53 | 0.53 | 61 | 1.65 | 0.29 | 3.45 |
| LOF (5) | Triple | Argon | | 1 2 | N | 33 | 0.53 | 0.53 | 60 | 1.65 | 0.29 | 3.45 |
| LOF (5) | Triple | Krypton | | 1 2 3 | N | 39 | 0.54 | 0.53 | 64 | 1.42 | 0.25 | 4.00 |
| LOF-LOF (3&5) | Triple | Arg/Kry | | 1 2 3 | N | 34 | 0.49 | 0.49 | 64 | 1.48 | 0.26 | 3.85 |
| LOF-LOF (3&5) | Triple | Argon | | 1 2 3 | N | 34 | 0.49 | 0.49 | 64 | 1.48 | 0.26 | 3.85 |
| LOF-LOF (3&5) | Triple | Krypton | | 1 2 3 | N | 40 | 0.50 | 0.49 | 68 | 1.25 | 0.22 | 4.55 |

(SHGC) Solar Heat Gain Coefficient: The higher the SHGC, the more solar heat the window allows.

(VT) Visible Transmittance: The higher the VT, the more daylight is allowed in.

(CR) Condensation Resistance: The higher the CR, the less likely condensations is to occur.